



PRODUCT SPECIFICATIONS

PRODUCT NAME: RUBBERSIL RS-200 G

CODE: SP- 207 -2

PHYSICAL AND CHEMICAL PROPERTIES	UNITS	LIMITS	GLASSVEN METHODS	INTERNATIONAL METHODS.
SiO ₂ Content, %	%	98 min.	MI-05 -033	ISO 3262/19
Loss on Drying (2 h @ 105°C)	%	3,0 – 6,0	MI-05-022	ISO 787/2
Loss on Ignition at 1050°C	%	4,0 - 6,0	MI-05-022	ISO 3262/19
pH Value (5% Slurry)	-	6,0 – 6,8	MI-05-025	ISO 787/9
BET Surface Area	m ² /g	170 – 200	MI-05-031	ISO 5794/1
DBP Oil Absorption	ml/100g	210 – 240	MI-05-029	ASTM D281-84
Sieve Residue on 50 mesh (>300 µm) RO-TAP	%	85,0 Min.	MI-05-028	ISO 787/7
Tapped Density	g/l	260 – 320	MI-05-027	ISO 787/11
Soluble Salts Content	%	3,5 Max.	MI-05-030	ISO 787/13

REGULATORY INFORMATION

CAS Registry: 112926-00-8 (7631-86-9)

EINECS Registry: 231-545-4

HANDLING AND STORAGE

HANDLING:

This product can be handled in the same way as any other inert product.

STORAGE:

The maximum length of storage time is twelve (12) months, after opened; controlling storage conditions, such as: moisture and temperature

Date of Issue:
June, 2008

Date of Next Issue:
December, 2011